














# transafe roadrail

VOYAGER<sup>™</sup> transafe

## voyager transafe

Heavy-duty ranges of safety flooring, available in a traditional or decorative multi-chip design. Voyager Transafe PUR features a high quality cross-linked polyurethane reinforcement, UV cured for improved maintenance and optimum appearance. Suitable for road vehicles and certain rail applications.

Gauge	ISO 24346 (EN 428)		2.0mm
Roll Length	ISO 24341 (EN 426)		2m x 20m = 40m <sup>2</sup>
Product Weight	ISO 23997 (EN 430)		2.0mm: 2430g/m <sup>2</sup>
General Performance	EN 13845 ASTM F1303		Conforms Conforms
Use Area Classification	ISO 10874 (EN 685)		23, 34, 43
Reaction to Fire	EN 13501-1 ISO 9239-1 Federal Motor Vehicle SS302 ASTM E648		Class Bfl-S1 >8.0Kw Conforms Class 1
Slip Resistance	DIN 51130 / DIN EN 16165 Ann. B AS 4586 EN 13845 RRL Pendulum Test (wet test -4S Rubber Slider/Slider 96) Surface roughness		R10 R10 ESf ≥36  Rz ≥20 μm
Abrasion Resistance	EN 13845		50,000 cycles
Binder Content	EN ISO 10581		Type I
Environment			100% Recyclable and contains recycled material
Maintenance Enhancement			Cross-linked polyurethane reinforcement
Hygiene			Voyager Transafe provides continuous, impervious and hygienic flooring which can be confidently cleaned in accordance with recommended maintenance procedures and approved maintenance products. The implementation of an effective cleaning regime is the most important defence against infection.
Resistance to Chemicals	ISO 26987 (EN 423)		Good
Notes			For information regarding handling and installation, adhesives, maintenance, and applications, consult Polyflor.  1 Slip resistance is assured throughout the guaranteed life of the product. For clarification, consult Polyflor  2 Safety flooring products should not have a polish applied.  3 Transafe has good resistance to dilute acids and alkalis. The Polyflor Technical Information Manual provides a general guide. Chemical resistance charts by shade are available on request.  4 Contact Polyflor to check availability of material in 2.5mm gauge



Decoration and shade may vary slightly from the samples shown.  
The data presented is correct at the time of printing.  
L'information présentée est valable au date d'imprimer.  
Sie geben nur einen kleinen Teil des gesamten Dekors und der Farbe wieder.  
Los datos presentados serán correctos en el momento de su impresión.

May 2022 V011/4